

## LUBRICATING GREASE

# **AUTHORIZED DISTRIBUTOR**

# NIPPON GREASE CO.,LTD.

Toyosaki Bldg., 18-21 Chayamachi Kita-ku Osaka〒530 TEL(06)373-0171 FAX(06)373-0174

# **CARTRIDGE LITHIUM EP-1**

**CARTRIDGE LITHIUM EP- 1** is non-lead EP lithium grease, consisting of highly refined base oil as base stock, thickened with lithium soap and effectively formulated of oxidation inhibitor, non-lead extreme pressure additive, rust preventive.

CARTRIDGE LITHIUM EP- 1 is suitable for lubrications of chassis of various automobiles from mini-size cars to extra large trucks, various construction machines, bearings, gears and pins, bearings for rolling stocks, and rolling/sliding bearings of various industrial machineries.

#### **♦** SPECIAL FEATURES

- 1. Has good mechanical stability and heat resistance.
- 2. Has strong water resistance.
- 3. Has good extreme pressure resistance.

### ♦ **APPLICATIONS**: Lubrication for;

- 1. Chassis of automobiles.
- 2. Bearings, gears, and pins of construction machineries.
- 3. Rolling or sliding bearings of general industrial machineries.

### **TYPICAL PROPERTIES**

| TEST ITEMS                |                        |        |                   | TEST METHOD    |
|---------------------------|------------------------|--------|-------------------|----------------|
| Appearance                |                        | ,      | Claybank-Butyroid | Visual         |
| Penetration, Worked 25 °C |                        |        | 365               | JIS K2220 5.3  |
| Dropping Point            |                        |        | 185               | JIS K2220 5.4  |
| Copper Corrosion          | B method<br>100°C 24 h |        | Pass              | JIS K2220 5.5  |
| Evaporation               | 99 ℃<br>22h            | mass % | 0.6               | JIS K2220 5.6  |
| Oil Separation            | 100°C<br>24h           | mass % | -                 | JIS K2220 5.7  |
| Oxidant Stability         | 99 ℃<br>100h           | MPa    | 0.029             | JIS K2220 5.8  |
| Worked Stability          | (10 <sup>5</sup> )     |        | 410               | JIS K2220 5.11 |
| Water Washout Test        | 38°C<br>1 h            | mass % | 3% 14             | JIS K2220 5.12 |
| Timken OK Load            |                        | kg     |                   | JIS K2220 5.16 |