

## NIPPON GREASE CO.,LTD.

Toyosaki Bldg., 18-21 Chayamachi Kita-ku Osaka 〒 530 TEL(06)373-0171 FAX(06)373-0174

## **SOLQUENCH WP5500**

**SOLQUENCH WP5500** is water base quenching fluid. It has high stability at high temperature and nice cooling rate for heat treatment parts. It compounds by high molecule polymer, anti-foam additive, anti bacteria additive, water, etc. It has no flame during quenching. It is fire safety product.

## **USE**

METHOD	MATERIAL	CONCENTATE	FLUID TEMPERATURE
Direct quenching	S35C – S55C	10 ~ 25 %	30 °C
Forging quenching	Alloy steel	10 ~ 30 %	30 °C

## **\*** CHARACTERISTIC

Density	15 °C	1.06
Color		Light yellow
Anti-rust test	10 %, cast iron 24 hr.	Pass
T'		N.T.
Fire point		None
Cooling speed	°C / see	
(400 – 150 °C)	10 %	342.5
	20 %	141.2